




Rec'd PCT/PTO 31 JAN 2005






**Indicator elements for autoclaves.**

**Patent number:** EP0282178  
**Publication date:** 1988-09-14  
**Inventor:** DOUGLAS MALCOLM FREDERICK  
**Applicant:** MINNESOTA MINING & MFG (US)  
**Classification:**  
- international: C09D11/00; A61L2/00  
- european: C09D11/00B, A61L2/28, G01N31/22F  
**Application number:** EP19880301279 19880216  
**Priority number(s):** GB19870004680 19870227

**Also published as:**

 US5057433 (A1)  
 JP63295686 (A)  
 EP0282178 (B1)

**Cited documents:**

 GB1132334  
 US3360337  
 US3360338  
 US3360339  
 FR1335076  
more >>

**Abstract of EP0282178**

An indicator element which provides a visual indication when subjected to correct steam sterilization conditions in an autoclave, the element comprising a substrate having coated thereon an ink formulation comprising as the primary visual change component:

- (i) a sulfur-containing compound capable of decomposition to yield a metal sulfide under steam sterilization conditions or,
- (ii) the precursors of such a sulfur-containing compound which will yield said sulfur-containing compound under aqueous conditions.

---

Data supplied from the **esp@cenet** database - Worldwide

**BEST AVAILABLE COPY**

⑫

**EUROPEAN PATENT APPLICATION**

⑲ Application number: 88301279.1

⑤① Int. Cl. 4: **C09D 11/00**, //A61L2/00

⑳ Date of filing: 16.02.88

③① Priority: 27.02.87 GB 8704680

④③ Date of publication of application:  
14.09.88 Bulletin 88/37

⑥④ Designated Contracting States:  
**DE FR GB IT**

⑦① Applicant: **MINNESOTA MINING AND  
MANUFACTURING COMPANY**  
**3M Center**  
**Saint Paul Minnesota 55144-1000(US)**

⑦② Inventor: **Douglas, Malcolm Frederick**  
**142 Pennard Drive**  
**Pennard Swansea, SA3 2DP Wales(GB)**

⑦④ Representative: **Bowman, Paul Alan et al**  
**LLOYD WISE, TREGEAR & CO. Norman**  
**House 105-109 Strand**  
**London WC2R 0AE(GB)**

⑤④ Indicator elements for autoclaves.

⑤⑦ An indicator element which provides a visual indication when subjected to correct steam sterilization conditions in an autoclave, the element comprising a substrate having coated thereon an ink formulation comprising as the primary visual change component:

(i) a sulfur-containing compound capable of decomposition to yield a metal sulfide under steam sterilization conditions or,

(ii) the precursors of such a sulfur-containing compound which will yield said sulfur-containing compound under aqueous conditions.

**EP 0 282 178 A1**

## INDICATOR ELEMENTS FOR AUTOCLAVES

The present invention relates to colour change indicator elements and in particular to colour change indicator elements which effect a colour change under sterilization conditions of high temperature and humidity effected during steam sterilization.

In hospitals, clinics and the like, it is standard practice to sterilize various products such as gowns, drapes, sheets, dressings, and other articles, prior to use by placing them in an autoclave where they are subjected to steam sterilization. This practice is necessary to avoid infection and prevent contamination from the use of such articles where the same are not in a sterile condition and it is particularly important where the articles have previously been used in the care of other patients. As there is no visual way of determining whether a particular article is sterile or not it has been the practice to use, with the article, when placed in the autoclave, a colour change indicator element which changes colour under the sterilizing conditions of the autoclave, thus indicating that the particular article or package has been passed through the sterilizing cycle. The indicator may be in the form of a ribbon or card to which a colour change ink has been applied.

It is generally the practice in sterilizing such articles to gather several articles together, bundling the same in a porous wrap, and then the package, held together by tying with string or by pressure-sensitive adhesive tape, is placed in an autoclave together with a sterilizing indicator element, the sterilization indicator element may be either inserted in or applied to the package. Where pressure-sensitive adhesive tapes are used for this purpose, it is convenient to have the colour change indicator on the tape backing. By observation of the visible back of the tape which holds the package together, one can readily determine by its colour change whether or not the same has been passed through the sterilization cycle. Pressure-sensitive adhesive tapes of this type are, for example, described in U.S. Patent No. 2,889,799.

Typical sterilization conditions comprise subjecting the articles to saturated steam at a temperature of between 132°C and 140°C, usually between 134°C and 140°C for a period of not less than 3 minutes. Another steam sterilization cycle comprises subjecting articles to 121°C for not less than 15 minutes. In order to ensure correct sterilizing conditions, the steam must penetrate unhindered to the centre of the load. This can be achieved only if all of the air is first removed from the sterilizer vessel and its load and this is accomplished typically by a process of evacuation and steam flushing of the sterilizing vessel and its load.

Failure to remove all of the air or the subsequent leakage of air into an evacuated chamber, or the introduction of air or non-condensable gases in the steam supply, causes gas pockets to remain within the porous load, usually in the inner regions thereof. In this case the temperature within the load might be lower in some places than that required during all or part of the sterilization process.

A standard test for the efficiency of air removal and/or the inclusion of non-condensable gases in autoclaves is known as the Bowie/Dick towel test. This test utilises a stack of standard linen Huckaback towels measuring some 270 mm high and about 300 mm x 200 mm in plan. At about the vertical centre of the stack there is placed a sheet of paper bearing so-called autoclave tape or other indicator which undergoes a change in appearance in the presence of certain levels of moisture and temperature. The test pack is processed in the autoclave and the satisfactory result would show an even change in appearance across the whole of the indicator sheet, whereas the presence of air or non-condensable gas in the stack is indicated by a failure of the indicator to change its appearance in certain areas, usually at the centre. This test must be carried out daily before the autoclave is used for the production of sterile porous loads.

There are certain disadvantages associated with this known test. For example, the standard towel stack is too large to fit into many small-chambered autoclaves. Furthermore, the Huckaback towels are expensive and usually require to be laundered at least once a week. The towels require to be aired carefully between tests and they deteriorate gradually and become unusable within about 12 months of normal use. This is because the fibrous consistency becomes matted so that steam cannot readily diffuse through it, thus increasing the risk of misleading test results. Furthermore, Huckaback towels, being made from natural fibre, can give rise to exothermic reactions, i.e. they will absorb moisture very readily with the release of heat, when they are too dry. In the case of the Bowie/Dick test such a phenomenon can result in the temperature within the pack being higher than the temperature in the autoclave chamber and again this can lead to misleading results.

British Patent Specification No. 2143322A discloses a test kit for detecting the presence of air in a steam sterilizer which comprises a first porous mass of at least substantially man-made material, a second porous mass of a similar material, an indicator adapted to undergo a visual change under moist heat sterilising conditions and sandwiched between the masses thus to be in intimate contact therewith, and means for removably holding the masses and indicator in close superimposed relationship, said means

being permeable to allow the free passage of air and steam to the external surfaces of said masses.

The test kit is generally in the form of a cuboid having a side dimension in the region of 12 to 15 cm and the indicator may conveniently comprise an autoclave tape or printed sheet having indicator in the shape of a St. Andrews cross or other pattern extending from side to side.

5 Experimental work has demonstrated that such a device as described is capable of detecting the presence of air in an autoclave. It is also clear from temperature measurements made within the device that the presence of air leads to a lower temperature at the centre of the test pack similar to that observed with the Huckaback towel pack used in the conventional Bowie/Dick test. The presence of air in the autoclave results in uneven change in the indicator, often incomplete colour change towards the centre of the device.

10 One of the most commonly used colour change media for use as an indicator contains sulphur and lead oxide. The sulphur in the presence of the lead oxide, under the conditions of the steam sterilization, changes from a yellow to a black colour as it is converted to lead sulphide. It has been the practice to mix the sulphur and the lead oxide together in equivalent molar proportions in an ink base which is then applied to an indicator card or to a back of a pressure-sensitive adhesive tape, which, in turn, is then associated  
15 with the articles to be sterilized. If the autoclave or other steam sterilizing equipment used is not functioning, or if the package to be sterilized inadvertently gets omitted from being placed in the autoclave, this can readily be determined by the fact that no reaction has occurred between the sulphur and the lead oxide as shown by the lack of colour change in the indicator. Similarly if air or non-condensable gas is present in the autoclave an incomplete reaction will occur in some areas resulting in incomplete generation of the black  
20 colour.

One difficulty with such inks is the tendency to stain when in contact with many articles. Staining can be the result of the transfer and reaction of sulphur as the formation of soluble materials during the colour change reaction staining causes unsightly marks on sheets and other articles which may prevent their use. Staining can be reduced by the provision of an overcoat over the printed ink requiring an extra processing  
25 step in the production of indicator elements thereby increasing the cost.

Another difficulty with the conventional sulphur lead oxide colour change inks is that they are relatively unstable, necessitating the practice of forming separate solutions of the sulphur and the lead oxide and then combining the two together just prior to using the ink for marking. This is apparently due to the fact that the sulphur and lead oxide tend to react while in the solvent medium used in forming the ink. If the ink solution  
30 is prepared several days prior to its use, a substantial reduction in colour change sensitivity results.

Where the colour change indicator is to be used in combination with a pressure-sensitive adhesive tape, as by printing the ink on the back of the tape, the inks containing the sulphur have the further disadvantage that the sulphur in the marking tends to migrate into the pressure-sensitive adhesive where the tape is wound on itself in roll form, thus further reducing the sensitivity of the marking to colour change, when the  
35 tape, which the ink marking thereon, is later exposed to steam sterilization conditions.

Although giving a good colour change from a light yellow to a deep black with fresh inks, the colour change indicator markings made from the active ingredients, lead oxide and sulphur, tend to lose much of their sensitivity over extended periods of storage. This is believed to be due to the oxidation of sulphur and is particularly prevalent under relatively hot conditions. Markings may not turn to the same deep black on  
40 being subjected to sterilizing conditions but tend to assume a dark grey appearance, with the result that the colour change is not nearly as marked as with fresh inks. This is particularly disadvantageous when the indicators are being used in testing the performance of an autoclave utilising the Bowie/Dick or similar test as misleading results may be obtained.

Despite these inherent disadvantages in colour change media using sulphur and lead oxide, such  
45 markings have continued to be widely used as steam sterilization indicators.

British Patent Specification No. 1211603 discloses an indicator material for determining whether steam sterilization has been applied comprising a mixture of lead carbonate and calcium sulphide. In the presence of steam at a temperature of about 120°C the calcium sulphide decomposes to form calcium hydroxide and hydrogen sulphide. The hydrogen sulphide in turn attacks lead carbonate to form black lead sulphide and  
50 carbonic acid.

Other known colour change indicators for indicating steam sterilization include e.g. the use of copper sulphite disclosed in U.S. Patent No. 3 360 339, which provides a colour change from red to green under steam sterilization conditions, and have not found commercial favour.

It has now been found that there are a number of sulphur-containing compounds which will decompose  
55 to yield a sulphide under steam sterilization conditions with a marked colour change.

According to the present invention there is provided an indicator comprising a substrate having coated thereon a formulation capable of undergoing a visual change upon being subjected to steam sterilization and which undergoes no visible change or a different visible change upon being subjected to conditions

milder than steam sterilization, the formulation comprising as the primary visual change component: (i) a sulphur-containing compound capable of decomposition to yield a metal sulphide under steam sterilization conditions or, (ii) the precursors of such a sulphur-containing compound which will yield said sulphur-containing compound under aqueous conditions.

5 Also according to the invention there is provided an ink formulation which when printed on a substrate is capable of undergoing a visual change upon being subjected to steam sterilization and which undergoes no visible change or a different visual change upon being subjected to conditions milder than steam sterilization, the formulations comprising a binder and as the primary visual change component (i) a sulphur-containing compound capable of decomposition to yield a metal sulphide under steam sterilization  
10 conditions, or, (ii) the precursors of such a sulphur containing compound which will yield said sulphur containing compound under aqueous conditions.

It has been found that there are a number of compounds having sulphur-containing radicals which will decompose to the metal sulphide under steam sterilization conditions with a pronounced colour change. Metal sulphides tend to be strongly coloured and are often the most stable form of metal sulphur-containing  
15 compounds. Furthermore, they are often insoluble in water and may be held in a binder to prevent staining. The preferred sulphur-containing radical is thiosulphate although other groups may be employed e.g. polythionates etc. Compounds for use as the primary colour change component include:

lead thiosulphate which is white in colour and decomposes to yield black lead sulphide under steam sterilization conditions,

20 copper thiosulphate which is yellow in colour and decomposes to yield black copper sulphide under steam sterilization conditions,

ferrous thiosulphate which is light green in colour and decomposes to yield a black sulphide under steam sterilization conditions,

25 nickel thiosulphate which is light green in colour and decomposes to black/green nickel sulphide under steam sterilization conditions,

cobalt thiosulphate which is light red/purple in colour and decomposes to deep purple/black cobalt sulphide under steam sterilization conditions,

bismuth thiosulphate which is orange/brown in colour and decomposes to black bismuth sulphide under steam sterilization conditions,

30 chromium thiosulphate which is grey/blue in colour and decomposes to dark green chromium sulphide under steam sterilization conditions.

It is also possible to employ precursors of such sulphur-containing compounds which will yield the sulphur-containing compounds under aqueous conditions. For example lead carbonate and sodium thiosulphate may be employed as the colour change component in the ink, these compounds undergoing a double  
35 decomposition reaction to yield lead thiosulphate under aqueous conditions. During the steam sterilization cycle lead thiosulphate is initially formed which then decomposes to lead sulphide providing the desired colour change.

The sulphur containing compounds or their precursors used in the invention may be employed as the sole colour change component and may be combined with a binder and solvent in an ink formulation. Such  
40 ink formulations may be readily prepared and tend to be physically and chemically stable on storage since the sulphur-containing compounds are stable at ambient temperature. The sulphur-containing compounds may also be used in combination with other components which aid or modify the colour generation under steam sterilization conditions. Other additives include carbonates, particularly lithium carbonate and magnesium carbonate. Such compounds may be used in formulation in amounts up to that of the lead  
45 thiosulphate. The selection of these materials is dependent upon the particular property required by the indicator tape. For example, it may be desirable to provide an indicator tape which will not undergo a substantial visual change unless it has been subjected to steam sterilization conditions for a certain period of time, e.g. two minutes.

The binder system for the ink formulations may comprise a film-forming carrier which is permeable to  
50 steam in order to obtain a satisfactory colour change under steam sterilization conditions. Binder systems based on nitrocellulose have been found to be particularly effective but many other binder systems may be used e.g. binder systems cured by ultraviolet irradiation or electron beam bombardment e.g. urethane-acrylates, epoxy-acrylates and polyester acrylates. Other binder systems include vinyl resins e.g. copolymers of polyvinyl chloride and polyvinyl acetate as disclosed in U.S. Patent No. 3360339.

55 The printing ink formulations may contain other additives, e.g. solvents, defoamers, flow aids and other printing aids.

The formulations are prepared by admixing the components of the binder system, solvent and colour change chemistry, e.g. in a mixer, ball mill or attriter. The binder system generally comprises from 50 to

98% by weight of the ink formulation and the colour change chemistry from 2 to 50% by weight of the ink formulation, usually in the range 20 to 35% by weight of the ink formulation.

A preferred ink formulation of the invention comprises

	general range	preferred
	% by weight	% by weight
5 10 lead thiosulphate	10 to 50	29
10 magnesium carbonate	0 to 10	1
n-propanol	0 to 30	10
15 n-propyl acetate	0 to 30	14
nitrocellulose binder	20 to 90	45

20 The indicators of the invention may comprise any substrate which is capable of withstanding steam sterilization conditions, i.e. a temperature of 121 to 138°C in the presence of steam for a period of up to 30 minutes. Suitable substrates include paper which may be absorbent or saturated with a rubber/resin solution or a natural or synthetic latex, coated paper, card, plastics material, metallised material, metal foil and non-woven or woven textile materials.

25 In one preferred form, the substrate is in the form of a tape, more preferably a pressure sensitive adhesive tape having a release coating upon one surface and a pressure sensitive adhesive on the other such that the tape may be wound in the form of a roll.

A second preferred form comprises a rectangular or square test sheet having an area on which the indicator has been applied of a side dimension in the range 10 to 15 cm for use in a Bowie/Dick test or 30 Lantor cube of the type disclosed in British Patent Specification No. 2143322A.

A particularly preferred form for use with the Lantor cube (commercially available from 3M UK PLC) comprises a paper sheet 30 cm by 15 cm, one half of the sheet having the indicator ink printed thereon (eg. in a pattern comprising a cross formed by diagonal lines extending from two corners and a series of chevrons formed of lines parallel to the cross) and the second half bearing printed matter for recording 35 details of the test, e.g. date, hospital, machine number, test results etc. The indicator paper is folded in half and placed between the blocks of the Lantor cube during testing.

Other substrates may be in the form of a bag or other wrapping in which case the printing ink formulation may be confined to small areas.

40 The ink formulations may be printed by a range of printing techniques, e.g. flexographic, rotogravure and screen printing, etc. The ink is generally applied in the form of patterns, e.g. stripes, chevrons, etc., in order to provide a visual contrast between areas of the indicator which will provide a visual change after steam sterilization and background areas of the indicator. However, the use of patterns is not essential and the indicator may be completely coated, e.g. by a web coating technique.

The invention will now be illustrated by the following Examples.

### 45 EXAMPLE 1

#### PREPARATION OF LEAD THIOSULPHATE

50 Concentrated nitric acid was added to distilled water to form a dilute solution. Lead carbonate was added slowly and the CO<sub>2</sub> effervescence allowed to die down before more was added. Lead carbonate was continually added until no more effervescence was observed. This indicated that a near neutral solution of lead nitrate was obtained. A solution of sodium thiosulphate was made up and when all of the crystals had 55 dissolved, this solution was poured into the solution of lead nitrate. Immediately a white precipitate of lead thiosulphate was formed. It was allowed to settle, the liquor poured off and fresh distilled water was stirred

in, the lead thiosulphate allowed to settle and the liquor again poured off. This washing process was again repeated. The slurry was then filtered through a Buchner funnel, the precipitate washed with more distilled water and then ethanol. Finally a wash with diethyl ether was made and the air pulled through the lead thiosulphate by the vacuum to dry off the ether.

5

## EXAMPLE 2

Three stock ink formulations were made up to the following formulation, which ingredients are  
10 expressed as parts by weight:

	<u>Ingredient/Ink</u>	A	B	C
15	lead thiosulphate	180	270	360
	n-propanol (solvent)	103	103	103
	n-propylacetate (solvent)	155.5	155.5	155.5
20	nitrocellulose binder	476	476	476
	Modaflow	3.1	3.1	3.1
25	Byke 141	1.6	1.6	1.6

The nitrocellulose binder used is commercially available from Fishburn Inks, Watford, England and is  
30 approximately 30% solids.

Modaflow is a flow aid commercially available from Monsanto.

Byke 141 is a defoamer commercially available from Byke-Chemie GmbH, Wesel, Germany.

The two solvents were added to the container of a laboratory air driven mixer, the mixer started and the  
35 lead thiosulphate added slowly. When this had evenly dispersed the binder was slowly poured in followed by the Modaflow and the Byke 141. The ink was then mixed for 20 minutes before use.

Each of the three inks was printed onto 80 gsm photocopy paper using a gravure foil, and dried at a temperature of 50°C.

Inks A1, B1 and C1 were prepared from inks A, B and C above by the addition of magnesium carbonate to each of the formulations in an amount of 12 parts by weight. Each of the inks A1, B1 and C1 were  
40 printed as described above.

Inks A2, B2 and C2 were prepared from inks A, B and C above by the addition of magnesium carbonate to each of the formulations in an amount of 24 parts by weight. Each of the inks A2, B2 and C2 were printed as described above.

Printed samples obtained with each of the ink formulations above were placed in a Lantor cube which  
45 was placed in an autoclave and subjected to steam sterilization for 3 minutes at 134°C.

The Lantor cube comprised two fibrous blocks essentially made of spun bonded polypropylene-sheets layered one upon another and held together in intimate contact by means of a porous shrink wrap film, said  
50 fibrous blocks being 15 cm by 15 cm by 7.5 cm. The two fibrous blocks are held together in intimate contact with the desired indicator between by means of a stainless steel clamp assembly which comprises two square end plates and two side panels which act as compression springs. The Lantor cube and clamp assembly are commercially available from 3M UK PLC.

In each case the printed samples exhibited a clear colour change from white to black and no staining of the cube took place. The clearest and darkest samples were those printed with formulations A2, B1 and B2.

Printed samples using inks B1 and B2 were placed in a Lantor cube and subjected to autoclaving as  
55 described above with the exception that air was deliberately introduced into the autoclave in an amount sufficient to provide a temperature difference of 0.5°C between the drain and the centre of the Lantor cube. This experiment was designed to represent a faulty autoclave having an air leak. The resulting samples exhibited full colour change at the edges of the sheet with areas of incomplete colour change towards the

centre thus indicating incomplete sterilization conditions.

### EXAMPLE 3

5

The following ink formulation was prepared

10	copper thiosulphate	300	g
	magnesium carbonate	12	g
	n-propanol	103	g
15	n-propyl acetate	156	g
	nitrocellulose binder	476	g
	Modaflow	3.1	g
20	Byke 141	<u>1.6</u>	<u>g</u>
	Total	<u>1051.7</u>	<u>g</u>

25

The ink was made exactly as described previously and printed as before onto photocopy paper. Testing entailed placing a 150 mm square sample into the Lantor cube and subjecting to steam sterilization at 134°C for 3 minutes.

30

It was noted that copper thiosulphate is apparently slightly unstable. When initially made it was a canary yellow colour, but when printed it was a yellow-light olive green colour which turns into a dense-black colour on autoclaving in the Lantor cube.

### EXAMPLE 4

35

LEAD NITRATE AND SODIUM THIOSULPHATE AS THE COLOUR CHANGE COMPONENTS IN AN AUTOCLAVE INK.

40

An autoclave ink of the following formulation was made by milling all of the components in a ball mill for about 16 hours.

	Lead nitrate	312	g
	Sodium thiosulphate	233	g
45	Magnesium Carbonate	12	g
	Nitrocellulose binder	476	g

50

55



n-propanol	103 g
n-propyl acetate	156 g
Modaflow	3.1 g
Byke 141	1.6 g

The ink was printed onto 80 gsm photocopy paper as previously described and then subjected to development in an autoclave for three minutes at 134°C with a sample of the sheet in a Lantor cube and in a stack of Huckaback towels as used for a Bowie and Dick test.

A clear colour change from white to black was observed in each sample.

#### EXAMPLE 5

#### EVALUATION OF ELEMENTAL THIOSULPHATES PRIMARY COMPONENT FOR VISUAL CHANGE IN- DICATING MEDIUM

The following materials were each weighed out as indicated and dissolved separately in distilled water in a test tube. A number of other test tubes containing 5g of sodium thiosulphate in distilled water were prepared. When the materials were totally in solution the thiosulphate was poured in turn until each of the other solutions to form the respective elemental thiosulphate, either in solution or as a precipitate. Bismuth thiosulphate was precipitated washed and dried to an orange/light brown powder.

Each solution was then boiled for a few minutes and the colour changed observed. Results are indicated in the following Table. In the case of bismuth thiosulphate, the solid was added to a test tube with some distilled water and was then boiled as before.

MATERIAL	QUANTITY g	COLOUR/PRECIPTATE WITH SODIUM THIOSULPHATE	COLOUR/PRECIPTATE WITH BOILING
Cerous nitrate	5.83	milky white	yellow precipitate
Caesium chloride	8.78	water white	water white
Cobaltous nitrate	5.86	light red/purple	deep purple/black
Bismuth nitrate	9.77	orange/brown precipitate	black precipitate
Stannous chloride	4.55	yellow/white	yellow/white
Barium nitrate	5.26	white precipitate	off white precipitate
Manganous chloride	3.98	water white	milky solution
Chromium nitrate	5.37	grey/blue (milky)	dark green
Nickel nitrate	5.86	light green	black/green
Ferrous sulphate	5.6	light green	black
Silver nitrate	6.84	brown precipitate	black precipitate

It can be seen from the Table that cobalt, bismuth, chromium, nickel, ferrous and silver thiosulphates provide a pronounced visual change and could be useful in an indicator ink system. The precursors of these compounds may also be used as a colour change component in indicator inks.

#### EXAMPLE 6

#### LEAD TETRATHIONATE AS COLOUR CHANGE COMPONENT IN AN AUTOCLAVE INK

Sodium thiosulphate solution was slowly added to a solution of blue capricnitrate trihydrate until the blue colour just disappeared. A solution of lead nitrate was then added to give an off-white precipitate of lead tetrathionate. The precipitate was allowed to settle, the liquor poured off and distilled water added with stirring. The precipitate was filtered, washed again with distilled water, methylated spirits and finally with

ether and thereafter dried.

50g of the lead tetrathionate was dispersed in 100g of the nitrocellulose binder used in Example 2 and the composition was hand spread onto sheets of 80gsm photocopy paper using No. 1 and No. 8 K Bars. The sheets were dried for 5 minutes at 50°C and then autoclaved for 3 minutes at 134°C. All samples developed a dark black colour.

## Claims

- 10 1. An ink formulation which when printed on a substrate is capable of undergoing a visual change upon being subjected to steam sterilization and which undergoes no visible change or a different visual change upon being subjected to conditions milder than steam sterilization, the formulation comprising a binder and a visual change component characterised in that the visual change component comprises:
  - (i) a sulphur-containing compound capable of decomposition to yield a metal sulphide under steam
  - 15 sterilization conditions or,
  - (ii) the precursors of such a sulphur-containing compound which will yield said sulphur-containing compound under aqueous conditions.
2. An ink formulation which when printed on a substrate capable of undergoing a visual change upon being subjected to steam sterilization and which undergoes no visible change or a different visual change
- 20 upon being subject to conditions milder than steam sterilization, the formulation comprising a binder and a visual change component characterised in that the visual change component comprises a sulphur containing compound capable of decomposition to yield a metal sulphide under steam sterilization conditions.
3. An ink as claimed in claim 1 or Claim 2 characterised in that the sulphur-containing compound is a thiosulphate selected from lead, copper, silver, bismuth, cobalt, chromium, nickel and ferrous thiosulphates.
- 25 4. An ink as claimed in Claim 1 or Claim 2 characterised in that the visual change component comprises lead nitrate and sodium thiosulphate.
5. An ink as claimed in any preceding claim characterised in that the binder comprises nitrocellulose.
6. An ink as claimed in Claim 1 or Claim 2 comprising
 

lead thiosulphate	10 to 50% by weight
30 magnesium carbonate	0 to 10% by weight
n-propanol	0 to 30% by weight
n-propyl acetate	0 to 30% by weight
nitrocellulose binder	20 to 90% by weight
7. An ink as claimed in Claim 6 comprising
 

35 lead thiosulphate	29% by weight
magnesium carbonate	1% by weight
n-propanol	10% by weight
n-propyl acetate	14% by weight
nitrocellulose binder	45% by weight
- 40 8. An indicator comprising a substrate having coated thereon a medium capable of undergoing a visual change upon being subjected to steam sterilization and which undergoes no visible change or a different visible change upon being subjected to conditions milder than steam sterilization characterised in that the medium comprises as the primary visual change component:
  - (i) sulphur-containing compound capable of decomposition to yield a metal sulphide under steam
  - 45 sterilization conditions or,
  - (ii) the precursors of such a sulphur-containing compound which will yield said sulphur-containing compound under aqueous conditions.
9. An indicator as claimed in Claim 8 characterised in that the medium capable of undergoing a visual change is obtained by application of an ink formulation as claimed in any one of Claims 1 to 7.
- 50 10. An indicator as claimed in Claim 8 or Claim 9 characterised in that substrate is selected from paper, saturated or coated paper, card, plastics material, metallised material, metal foil and woven and non-woven textile materials.
11. An indicator as claimed in any one of Claims 8 to 10 characterised in that the medium is overcoated with a release coating and the opposite surface of the substrate is coated with a pressure sensitive
- 55 adhesive.
12. An indicator as claimed in any one of Claims 8 to 11 in the form of a rectangle or square having a side dimension of from 10 to 15 cm.

13. An Indicator as claimed in any one of Claims 8 to 11 in the form of a rectangle having side dimensions 30 cm by 15 cm, one half of the rectangle having said medium thereon, optionally in the form of a pattern.

5

10

15

20

25

30

35

40

45

50

55



European Patent  
Office

# EUROPEAN SEARCH REPORT

Application Number

EP 88 30 1279

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl.4)
A	CHEMICAL ABSTRACTS, vol. 93, 1980, page 97, no. 206328s, Columbus, Ohio, US; & JP-A-80 18 269 (MASUDA et al.) 17-05-1980 ---		C 09 D 11/00 // A 61 L 2/00
A	GB-A-1 132 334 (ES & A ROBINSON) ---		
A	US-A-3 360 337 (M.I. EDENBAUM) ---		
A	US-A-3 360 338 (M.I. EDENBAUM) ---		
A,D	US-A-3 360 339 (M.I. EDENBAUM) ---		
A	FR-A-1 335 076 (TEMPIL CORP.) -----		
			TECHNICAL FIELDS SEARCHED (Int. Cl.4)
			C 09 D
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 03-06-1988	Examiner GIRARD Y.A.
<b>CATEGORY OF CITED DOCUMENTS</b>			
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons ----- & : member of the same patent family, corresponding document	

**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**